

LATEX CONCENTRATE

HA Latex 60% DRC

High-ammonia latex concentrate at 60.0% DRC with MST minimum 650 s for dipped goods and gloves.

LA 60

Dipped goods



- 60.0% dry rubber content plus or minus 0.5%
- 205 L drums or 20 MT flexitanks
- MST minimum 650 s, VFA at or below 0.06%
- Specified for medical and industrial glove lines

SPECIFICATIONS

Dry rubber content (DRC)	60.0% ± 0.5% dry rubber content	Minimum order	20 MT (flexitank or 205 L drums)
Ammonia content (NH3)	0.6–0.8% ammonia on total weight	Packaging	205 L steel drums or 20 MT flexitank
Mechanical stability time (MST)	min. 650 s mechanical stability time	Lead time	2–3 weeks FOB Belawan / Jakarta
Volatile fatty acids (VFA)	≤ 0.06% volatile fatty acids		

EXPORT DETAILS

HS CODE	INCOTERMS	CERTIFICATIONS		
4001.10	FOB · CIF · CFR	ISO 9001	ISO 14001	Halal (BPJPH)

PRODUCT OVERVIEW

HA latex at 60.0% dry rubber content for glove, condom, and dipped-goods plants. Ammonia is held between 0.6 and 0.8% on total weight, mechanical stability time exceeds 650 seconds, and volatile fatty acids stay at or below 0.06%. Available in 205 L drums or 20 MT flexitanks.

Values are typical specifications for the current production period and are confirmed lot by lot on the sales contract. Laboratory records travel with every shipment.

PT FoodHub Collective Indonesia

Jl. Tb Simatupang Kav. 1, Pasar Minggu
Jakarta Selatan 12560, Indonesia

sales@indonesia-rubber.com

+62 896 7558 3987
indonesia-rubber.com



Scan for the full
product page