

TSR BALE

## SIR 3L Light Color TSR

Field-latex Indonesian TSR with dirt at or below 0.03%, PRI at or above 60, Mooney ML 50 plus or minus 5.

SIR 3L

Tire



- Lightest-color TSR band from field-latex feedstock
- PRI at or above 60 for oxidative stability
- Dirt at or below 0.03%, ash at or below 0.50%
- Scheduled production, three to four week lead time

### SPECIFICATIONS

|                                  |               |                  |                                                             |
|----------------------------------|---------------|------------------|-------------------------------------------------------------|
| Dirt content                     | ≤ 0.03% (w/w) | Mooney viscosity | ML (1+4) 100 °C: 50 ± 5                                     |
| Ash content                      | ≤ 0.50% (w/w) | Minimum order    | 19.6 MT (1 × 20 ft FCL, 560 bales)                          |
| Volatile matter                  | ≤ 0.80% (w/w) | Packaging        | 35 kg bales, shrink-wrapped pallet (1,260 kg N.W. per unit) |
| Nitrogen                         | ≤ 0.60% (w/w) | Lead time        | 3–4 weeks FOB Jakarta / Belawan                             |
| Plasticity retention index (PRI) | ≥ 60          |                  |                                                             |

### EXPORT DETAILS

|         |                 |                |          |           |           |               |
|---------|-----------------|----------------|----------|-----------|-----------|---------------|
| HS CODE | INCOTERMS       | CERTIFICATIONS |          |           |           |               |
| 4001.22 | FOB · CIF · CFR | SNI 1903       | ISO 9001 | ISO 14001 | ISO 45001 | Halal (BPJPH) |

### PRODUCT OVERVIEW

SIR 3L is the lightest-color Indonesian TSR grade in our catalogue, milled from field latex and fresh coagulum streams. Dirt content is at or below 0.03%, ash at or below 0.50%, and PRI is at or above 60. Mooney ML (1+4) at 100 °C centres at 50 for premium tread and specialty compounds that name light TSR on the purchase order.

Values are typical specifications for the current production period and are confirmed lot by lot on the sales contract. Laboratory records travel with every shipment.

PT FoodHub Collective Indonesia

Jl. Tb Simatupang Kav. 1, Pasar Minggu  
Jakarta Selatan 12560, Indonesia

sales@indonesia-rubber.com

+62 896 7558 3987  
indonesia-rubber.com



Scan for the full  
product page